

ITALFIX

Reactive Dyes



NK ITALIA

A horizontal graphic element representing the Italian flag, consisting of three equal-width vertical stripes of green, white, and red.



NK ITALIA

P&H Dyes

4%

GOLDEN YELLOW HR
(Orange 12)



ORANGE H2R
(Orange 13)



RED H8B
(Red 31)



RED H2B
(Red 45)



BLUE H5R
(Blue 13)



BLUE H3R
(Blue 49)



VIOLET H1R
(Violet 1)



BLACK HN
(Black 8)



General Properties					Washing ISO 105 CO4		Perspiration		Hypochlorite	
Solubility 30°C	Substantivity	Reactivity	Fixation Temp	Light Fastness 1/1	Effect	Stain	Effect	Stain	Effect	Stain
100	M	M	80	4-5	5	5	4	5	3	4-5
80	M	M	80	4	4-5	4	4-5	4	4	4-5
80	M	L	80	4-5	4-5	4	4	3-4	1	4-5
100	M	L	80	5	4	4	4	4-5	1	4-5
70	M	L	80	4-5	4	4-5	4-5	4	1	4-5
80	M	M	80	4-5	4-5	5	4	3-4	3-4	4-5
75	M	M	80	5	5	4-5	3-4	4	4	4-5
80	M	M	80	5	4-5	5	4-5	3-4	3	4-5




NK ITALIA


VS Dyes

4%


YELLOW FG
(Yellow 42)



GOLDEN YELLOW RNL
(Orange 107)




ORANGE 2G
(Orange 72)




ORANGE 3R
(Orange 16)



RED BS
(Red 111)




RED RB
(Red 198)



VIOLET 5R
(Violet 5)



BROWN GR
(Brown 18)



General Properties					Washing ISO 105 CO4		Perspiration		Hypochlorite	
Solubility 30°C	Substantivity	Reactivity	Fixation Temp	Light Fastness 1/1	Effect	Stain	Effect	Stain	Effect	Stain
100	H	M	60	4-5	5	5	5	4-5	1	4
100	H	M	60	5	4	4	3-4	4-5	5	3-4
75	H	L	60	4-5	4-5	4	4-5	4-5	4-5	4
80	M	M	60	5	4-5	4-5	3	3-4	3-4	5
100	S	M	60	4-5	3-4	5	4	5	2	4
100	M	M	60	4-5	4-5	5	4	5	1	4
70	H	M	60	5	4	4-5	4-5	4-5	5	3-4
80	M	M	60	4	4-5	4-5	4	4-5	5	4




NK ITALIA


VS Dyes

4%


TURQUOISE G
(Blue 21)



BLUE BB
(Blue 220)




NAVY BLUE RGB
(Blue 250)




BLACK B
(Black 5)



BLACK RL
(Black 31)




BLACK N-150



BLACK WNN



BLACK HFGR



General Properties					Washing ISO 105 CO4		Perspiration		Hypochlorite	
Solubility 30°C	Substantivity	Reactivity	Fixation Temp	Light Fastness 1/1	Effect	Stain	Effect	Stain	Effect	Stain
75	H	M	80	4-5	4-5	5	5	4-5	3-4	5
100	H	M	60	5	4-5	4-5	5	3-4	3-4	5
100	H	M	60	5	4-5	4-5	4-5	4-5	4-5	4-5
100	H	H	60	4-5	4-5	4-5	5	4	5	5
100	L	L	60	4-5	4	4	4	5	4	4
100	H	H	60	4-5	4-5	4-5	5	5	1	4-5
100	S	M	60	5	4-5	5	4-5	5	1	5
100	S	H	60	5	4-5	4	5	4	3-4	4




NK ITALIA


ME Dyes

4%


YELLOW ME4GL
(Yellow 160)




YELLOW MERL
(Yellow 145)



YELLOW 3RS
(Yellow 176)




ORANGE ME2RL
(Orange 122)




RED ME3BL
(Red 194)




RED ME4BL
(Red 195)



BLUE MERF
(Blue 221)



NAVY BLUE MEBL
(Blue 222)



General Properties					Washing ISO 105 CO4		Perspiration		Hypochlorite	
Solubility 30°C	Substantivity	Reactivity	Fixation Temp	Light Fastness 1/1	Effect	Stain	Effect	Stain	Effect	Stain
100	H	L	60	4	4-5	4	4-5	4-5	4-5	4-5
100	H	L	60	5	4-5	4-5	3-4	3-4	4-5	5
100	H	L	60	4-5	4	4-5	4	4	1-2	4-5
80	H	L	60	4	4-5	4	4	4	5	5
80	H	L	60	4-5	4-5	4-5	4	3	4-5	4-5
100	H	L	60	4	4-5	4-5	4	4	4-5	5
80	H	L	60	4	4-5	4-5	5	5	4-5	4
80	H	L	60	5	4-5	4-5	4-5	4-5	4	5




NK ITALIA


HE Dyes

4%


GOLDEN YELLOW HE4R
(Yellow 84)




ORANGE HER
(Orange 84)




RED HE3B
(Red 120)




RED HE7B
(Red 141)




RED HE8B
(Red 152)




BLUE HERD
(Blue 160)



BLUE HEGN
(Blue 198)



NAVY BLUE HER
(Blue 171)



General Properties					Washing ISO 105 CO4		Perspiration		Hypochlorite	
Solubility 30°C	Substantivity	Reactivity	Fixation Temp	Light Fastness 1/1	Effect	Stain	Effect	Stain	Effect	Stain
100	H	H	80	4-5	4-5	5	4-5	4-5	-	2-3
80	H	H	80	4	4	5	4	4	-	4-5
80	H	H	80	5	5	5	4-5	5	-	3-4
80	H	H	80	4-5	4-5	4-5	5	4-5	-	3-4
80	H	H	80	4-5	5	4	5	4-5	-	3-4
75	H	H	80	4-5	4-5	4-5	4-5	4	-	1
75	H	H	80	4-5	4-5	4-5	4-5	4-5	-	1
75	H	H	80	4-5	4-5	4-5	4-5	4	-	1-2



NK ITALIA

www.nkgroup.it

NK ITALIA SRLS

Via Monte Grappa, 7

21048 Solbiate Arno

(Varese) – ITALY

nkitalia@nkgroup.it